

# PAINT PROTECTION FILM

## Matte



### Performance Properties

<b>Thickness</b> without liner or cap sheet	7-8 mil
<b>Rock Chip Resistance</b> Water-worn road gravel, 9.5 mm to 16 mm mesh (SAE J400 Gravelometer, ASTM D3170-12)	Pass
<b>Chemical Resistance</b> Isopropyl Alcohol & Heptane/Hexane/MEK (ASTM D7244, ASTM D6279)	No Detrimental Effect
<b>Weathering</b> QUV & Xenon, up to 2500 hrs (ASTM G153 & ASTM G155)	No Detrimental Effect
<b>Staining</b> Transmission Fluid, Antifreeze, Windshield Washing Fluid & Used Motor Oil, Ketchup, Mustard (ASTM E313-98)	Resilient
<b>Acid Immersion</b> 10% Sulfuric Acid, 72 hrs	No Detrimental Effect
<b>Base Immersion</b> 10% Sodium Hydroxide, 72 hrs	No Detrimental Effect